
TYGON® ND Series



PERFORMANCE PLASTICS

Saint-Gobain Performance Plastics, a world leader in the development of higher performance polymer products, offers a new alternative to DEHP-plasticized PVC.

Medical Grade Vinyl Tubing Products

From blood and IV bags to enteral feeding, ECMO and dialysis tubing, polyvinyl chloride (PVC) is widely used throughout the healthcare industry. However, ongoing studies of di (2-ethylhexyl) ester (DEHP), a phthalate plasticizer commonly used in flexible PVC products, have raised concerns regarding its use in medical applications. In response to these changing needs, the Saint-Gobain R&D team has formulated a complete range of non-DEHP plasticized materials that meet DEHP performance criteria for critical attributes including clarity, flexibility, chemical resistance, bondability and shelf life.

Biocompatibility

TYGON® ND Series tubing products were developed specifically for use in medical applications. All formulations are USP Class VI approved. Additionally, the ND 100-65 material carries a full complement of biocompatibility testing, including pyrogenics, hemolytics and toxicity.

Non-DEHP and REACH Compliance

Based upon a unique chemistry developed by Saint-Gobain, TYGON® ND Series tubing was formulated to be Registration, Evaluation, Authorization and restriction of CHemical (REACH) compliant for DEHP. To ensure compliance, every individual compound lot is tested to ensure DEHP levels are <1000 ppm. During the extrusion process, individual product dimensions are maintained and monitored through in-line micrometers and off-line verification with computerized imaging equipment.

Typical Applications

- Dialysis equipment Minimally invasive devices
- Peristaltic pumps
 Inhalation equipment
- Medical laboratories Blood and IV solutions



TYGON® ND 100 Series Plasticizer: TOTM

Shelf Life: 3 years

Product	Durometer Hardness, Shore A, 15 sec	Color	Tensile Strength, psi (MPa)	Ultimate Elongation, %	Tear Resistance Ib f/in (kN/m)	Specific Gravity	Water Absorption, % 24 hrs. @23°C	Compression Set Constant Deflection, % @ 158°F (70°C) for 22 hours
ASTM Method	D2240	-	D412	D412	D1004	D792	D570	D395
ND 100-40	40	Clear	1225 (8.4)	380	70 (12.3)	1.13	0.17	53
ND 100-55	55	Clear	1725 (11.9)	425	145 (25.4)	1.18	0.14	57
ND 100-65	65	Clear	2075 (14.3)	415	185 (32.4)	1.19	0.12	60
ND 100-70	70	Clear	2300 (15.90)	415	210 (36.8)	1.19	0.12	60
ND 100-80	80	Clear	2625 (18.1)	350	275 (48.2)	1.21	0.12	59
ND 100-40	replaces Tygon® S-	40-HL	/ ND 100-	-65 replaces Tygo	in® S-50-HL	/ ND	100-80 replaces	Tygon® S-54-HL

TYGON® ND 200 Series Plasticizer: DINCH

Shelf Life: 3 years

Product	Durometer Hardness, Shore A, 15 sec	Color	Tensile Strength, psi (MPa)	Ultimate Elongation, %	Tear Resistance Ib f/in (kN/m)	Specific Gravity	Water Absorption, % 24 hrs. @23°C	Compression Set Constant Deflection, % @ 158°F (70°C) for 22 hours
ASTM Method	D2240	-	D412	D412	D1004	D792	D570	D395
ND 200-40	40	Clear	1125 (7.8)	370	60 (10.5)	1.09	0.20	49
ND 200-55	55	Clear	1625 (11.2)	385	120 (21.0)	1.14	0.16	52
ND 200-65	65	Clear	2000 (13.8)	385	155 (27.1)	1.17	0.15	57

TYGON® ND 300 Series Plasticizer: DOA

Shelf Life: 1 year

Product	Durometer Hardness, Shore A, 15 sec	Color	Tensile Strength, psi (MPa)	Ultimate Elongation, %	Tear Resistance Ib f/in (kN/m)	Specific Gravity	Water Absorption, % 24 hrs. @23°C	Compression Set Constant Deflection, % @ 158°F (70°C) for 22 hours
ASTM Method	D2240	-	D412	D412	D1004	D792	D570	D395
ND 300-40	40	Clear	1075 (7.4)	435	55 (9.6)	1.10	0.29	55
ND 300-55	55	Clear	1575 (10.9)	435	100 (17.5)	1.14	0.24	60
ND 300-65	65	Clear	1900 (13.1)	415	155 (27.1)	1.16	0.24	59

Shore A Hardness was measured on 1/4 in. buttons
Unless otherwise noted, all tests were conducted at room temperature (73°F). Values shown were determined on 0.075" thick molded ASTM plaques or molded ASTM durometer buttons.

Global Presence, Local Resource



leading producer of engineered, highperformance polymer products. Our core competency lies in our process technologies technologies that transform difficult-toprocess materials into useful products for industry. These materials include fluoropolymers (PTFE, PFA and FEP), silicone rubber and a range of other high-performance engineered polymers. Our tradition of excellence goes back more than 300 years through our parent company, Compagnie de Saint-Gobain, one of the world's top 100 industrial corporations, with operations in more than 60 countries. We leverage our global technology to provide worldwide advanced materials research, polymer processing and

Saint-Gobain Performance

Plastics is the world's

Saint-Gobain Performance Plastics — Portage 2316 W. Wisconsin Street Portage, WI 53901

Tel: (800) 236-7600 Tel: (608) 742-8541 Fax: (608) 742-4731

Saint-Gobain Performance Plastics — Akron

2664 Gilchrist Road Akron, OH 44305 Tel: (800) 798-1554 Tel: (330) 798-9240 Fax: (330) 798-6968

Saint-Gobain Performance Plastics — Beaverton 3910 Terry-Diane Street Beaverton, MI 48612 Tel: (888) 387-0067 Tel: (989) 435-9533 Fax: (989) 435-2355

Saint-Gobain Performance Plastics — Clearwater 4451 110th Avenue North Clearwater, FL 33762 Tel: (800) 541-6880 Fax: (727) 530-5603

Saint-Gobain

Performance Plastics — Taunton 700 Warne<u>r Blvd.</u> Taunton, MA 02780 Tel: (800) 722-7106 Tel: (508) 823-7701 Fax: (508) 823-1438

Saint-Gobain

Performance Plastics — Charny La Mothe-aux-Aulnaies Tel: (33) 3-86-63-78-78 Fax: (33) 3-86-63-77-77

Saint-Gobain Performance Plastics — Neuss Borsigstrasse 13-15 D-41469

Tel.: +49 (o) 2137-91789-11 Fax: +49 (o) 2137-12667

Saint-Gobain

Performance Plastics — Bangalore Grindwell Norton Ltd, Devanahalli Road, Off Old Madras Road, Bangalore, 560049, India Tel: +91 80 28472900 Fax: +91 80 280472616

Saint-Gobain

Performance Plastics — Lyon
Zone Industrielle de Chesnes - B.P 712 F-38297 Saint-Quentin Fallavier Cedex, France Tel: (33) 474 948 222 Fax: (33) 474 942 341

Saint-Gobain

Performance Plastics — Suwa 10801-5, Haramura, Suwa-gun Nagano 391-0106 Japan Tel: (81) 266-79-6400 Fax: (81) 266-70-1001

Saint-Gobain Performance Plastics — Shanghai 1468 Kun Yang Road, Minhang Economic & Technological **Development Zone** Shanghai, China 200245 Tel: (86) 21 5472 1568 Fax: (86) 21 5472 2378/5472 2379



TYGON® tubing is not intended for use as an implant material.

Saint-Gobain Non-DEHP tubing contains DEHP levels of <1000 ppm.

TYGON® is a registered trademark.

IMPORTANT: It is the user's responsibility to ensure the suitability and safety of Saint-Gobain Performance Plastics tubing for all intended uses. Laboratory and clinical tests must be conducted in accordance with applicable regulatory requirements in order to determine the safety and effectiveness for use of tubing in any particular application.

For a period of 6 months from the date of first sale, Saint-Gobain Performance Plastics Corporation warrants this product to be free from defects in materials and workmanship. Our only obligation will be to replace any portion proving defective, or at our option, to refund the purchase price thereof. User assumes all other risk, if any, including the risk of injury, loss or damage, direct or consequential, arising out of the use, misuse, or inability to use, this product. THIS WARRANTY IS IN LIEU OF THE WARRANTIES OF MERCHANTABILITY, FITNESS FOR PARTICULAR PURPOSE, AND ALL OTHER WARRANTIES, EXPRESSED OR IMPLIED. No deviation is authorized.

Saint-Gobain Performance Plastics Corporation assumes no obligations or liability for any advice furnished by it, or for results obtained with respect to those products. All such advice is given and accepted at the buyer's risk.





manufacturing support

unmatched by any

competitor.